

TECHNICAL DATA



PLANK SPECIFICATION	TEST METHOD	SINGLE PLANK
Length ± 5mm		1820mm 72"
Width ± 0.2mm	EN 13489	190mm 7 1/2"
Total thickness ± 0.1mm		14.2mm 9/16"
Top layer		3.2mm, 6.02mm
Squareness	EN 13489	≤0.2% Over the width
Cup	EN 13489	≤0.2% Over the width
Spring	EN 13489	≤0.1% Over the length
Lipping	EN 13489	≤0.2mm
Moisture Content	EN 13183-1	7% ± 2% (at the time of delivery)
Adhesive	EN 717-1	JAPAN F☆☆☆☆~ SEO
Finishing	BONA	7 Coats of abrasion resistance ASTM S33 > 100 revolutions
	KLUMPP	7 Coats of abrasion resistance ASTM S33 > 100 revolutions
	KLUMPP EMO	3 Coats
Formaldehyde Emissions	ASTM D5116-NAF	ZERO EMISSIONS / NO ADDED FORMALDEHYDE

